

SEED OR SOD EDGES. ENSURE ADJACENT MATERIAL IS FLUSH WITH CONCRETE AND GENTLY SLOPES AWAY AT EDGE

LIGHT BROOM FINISH TOOLED EDGES (ALL POURS)

150mm POURED IN PLACE CONCRETE PAD MINIMUM 25MPa @ 28 DAYS, 5-7% AIR ENTRAINMENT INTEGRALLY MIX FIBRE MESH REINFORCING AT A RATE OF 0.6kg/m³

MINIMUM 200mm COMPACTED DEPTH OF GRANULAR 'A' COMPACTED TO 98% S.P.D. COMPACTED SUBGRADE TO 98% S.P.D.

NOTES:

- 1. EXCAVATE TO MINIMUM DEPTHS, CONTRACTOR SHALL BE RESPONSIBLE FOR THE REMOVAL AND REPLACEMENT OF ANY UNSUITABLE SUBGRADE MATERIAL SUCH AS TOPSOIL. REMOVE ALL EXCAVATED MATERIAL AND DISPOSE OF OFF SITE.
- 2. SLOPE SUBGRADE PARALLEL TO FINISHED GRADE (MIN. 2% SLOPE AWAY FROM EXISTING BUILDINGS).
- ALL CONCRETE WORK TO TOWN STANDARDS OR BETTER.
- 4. EXPANSION JOINTS EVERY 6.0m MAX AND CONTROL JOINTS EVERY 1.5m MAX WITH SAW CUTS TO A DEPTH OF 45mm.
- 5. 10mm NON EXTRUDING BITUMINOUS FIBRE TO BE USED BETWEEN POURS. FILL 150mm DEEP.
- SPRAY WITH WHITE PIGMENT CURING COMPOUND WITHIN 3hrs.
- 7. PROTECT WET CONCRETE UNTIL HARD ENOUGH TO WITHSTAND MARKING. CORRECT ANY DAMAGED AREAS WITH REMOVAL AND REPLACEMENT OF CONCRETE AT CONTRACTOR'S EXPENSE.
- 8. IN ALL AREAS WHERE NEW SOD IS TO BE LAYED, ENSURE SOD IS FLUSH WITH CONCRETE SURFACE. SOD MUST NOT BLOCK SURFACE DRAINAGE.
- 9. WIDTH OF PATH OR SIZE OF CONCRETE PAD AS PER PLAN OR CONFIRMED ON SITE.
- 10. ADJACENT GRADES ARE TO SLOPE AWAY FROM THE TRAIL.

TOWN OF CALEDON					APR'D: APR'D DATE:AU	IGUST 17
POURED IN PLACE					DRAWN: KY SCALE:	scale: NTS
CONCRETE	1.	RECREATED.		APR 19	STANDARD No. 902	
	NO.	REVISION	APR'D	DATE		